

Release Agents (Non-Petroleum) - For Use In Dump Beds Hauling Hot Mix Asphalt

Supplier	Brand
Arrow Magnolia International Dallas, TX	Super Slick
BG Chemical, LP Dallas, TX	Black Magic GreenGuard Loose Juice
Brody Chemical Salt Lake City, UT	Top Shelf
ChemStation Mid-South Memphis, TN	8277
ChemStation of the Ozarks Springdale, AR	8277
ChemStation Dayton, OH	22172 41470C
Chemtek Inc. Research Triangle Park, NC	BA-30 PavePro Blue
Citrus Depot St. Petersburg, FL	CK Release Agent
Emulso Tonawanda, NY	AR-92

Release Agents (Non-Petroleum) - For Use In Dump Beds Hauling Hot Mix Asphalt

Supplier	Brand
Industrial Oils Unlimited, LLC Tulsa, OK	Asphalt Release Agent PR
KO Manufacturing, Inc. Springfield, MO	Polymeric Release Agent, Formula 4014
Meyer Laboratory, Inc. Blue Springs, MO	Avalanche
	Super Slider
	Ultra Slider
SoySolv Biosolvents, LLC Cleveland, OH	TackSolv
ZEP Inc. Atlanta, GA	BMF
	No. 1
	Pinnacle

Method of Documentation of Acceptance:

By brand and source.

Method of Approval:

**THE PROCEDURE BELOW MUST BE FOLLOWED IN ACQUIRING
APPROVAL OF MATERIALS TO BE ADDED TO THE
ABOVE QUALIFIED PRODUCTS LIST:**

- The manufacturer/supplier shall submit a 1 quart sample, the Safety Data Sheet (SDS) and product information, including printed instructions for application. Submitted

Release Agents (Non-Petroleum) - For Use In Dump Beds Hauling Hot Mix Asphalt

information shall indicate in writing that the release agent is non-carcinogenic, environmentally safe, and contains no flammable materials, solvents or petroleum elements.

- The manufacturer/supplier shall supply results of current AASHTO Product Evaluation & Audit Solutions (formerly National Transportation Product Evaluation Program (NTPEP)) testing and shall furnish a written statement that the submitted product is identical to that most recently tested by AASHTO. The AASHTO results shall meet the following minimum requirements:

- 7-Day Stripping Test at full strength shall indicate no stripping or discoloration.
- Asphalt Pull Off Test shall leave a residue of not more than 10 percent after three repetitions.

- If the asphalt release agent meets the performance criteria, a letter and unsigned certification agreement will be sent to the manufacturer. The product will be placed on the QPL upon receipt of the signed certification agreement.

- The product must be resubmitted to AASHTO for full testing every 5 years, or if a change in formulation, composition, or physical properties of the product occurs.

- Destination samples will be taken as deemed necessary by the Materials Engineer to assure compliance with specifications. Failure of these samples either in the laboratory or in field applications is sufficient reason to reconsider acceptance of the material. Suspension of further use and/or removal from the QPL may occur until the Materials Engineer determines that the product is in compliance with applicable specifications and requirements.

- The product shall not be detrimental to bituminous mixtures and will not dissolve asphalt cement at any dilution rate (minimum dilution of 0% to the maximum dilution recommended by the manufacturer) and will leave no residue that is a hazardous waste.

- The product shall be a non-solvent and non-petroleum based product. It shall be non-carcinogenic, environmentally safe, water soluble, and contain no solvents or petroleum hydrocarbons.

The manufacturer of privately labeled products must be disclosed.

No information contained in these lists is to be used for promotional purposes.