



ARKANSAS DEPARTMENT OF TRANSPORTATION

AR DOT.gov | I Drive Arkansas.com | Lorie H. Tudor, P.E., Director

MATERIALS DIVISION

11301 West Baseline Road | P.O. Box 2261 | Little Rock, AR 72203-2261 | Phone: 501.569.2185 | Fax: 501.569.2368

November 17, 2021

TO: Mr. Chad Adams, District 4 Engineer

SUBJECT: Job No. 040837
Bloomer – Franklin Co. Line
Route 22 Section 1
Sebastian County

Attached is the requested Pavement Sounding information and core photos for the above referenced job. These samples were requested via email by Marcus Rainwater October 7, 2021. The proposed project will mill and inlay the main lanes of Highway 22, then overlay the entire roadway section. Cores were taken at ¼ mile increments, alternating lanes. Cores were obtained from the existing travel lanes and shoulders.



Jonathan A. Annable
Materials Engineer

JAA:yz:bjj

Attachment

cc: Program Management
Roadway Design
System Information and Research
G. C. File

ARKANSAS STATE HIGHWAY AND TRANSPORTATION DEPARTMENT - LITTLE ROCK, ARKANSAS
MATERIALS DIVISION

JONATHAN A. ANNABLE, MATERIALS ENGINEER

*** SOIL SURVEY / PAVEMENT SOUNDING TEST REPORT ***

DATE	- 11/05/21	SEQUENCE NO.	- 1
JOB NUMBER	- 040837	MATERIAL CODE	- PSO
FEDERAL AID NO.	- TO BE ASSIGNED	SPEC. YEAR	- 2014
PURPOSE	- SOIL SURVEY SAMPLE	SUPPLIER ID.	- 1
SPEC. REMARKS	- NO SPECIFICATION CHECK	COUNTY/STATE	- 65
SUPPLIER NAME	- STATE	DISTRICT NO.	- 04
NAME OF PROJECT	- BLOOMER - FRANKLIN CO. LINE		
PROJECT ENGINEER	- NOT APPLICABLE		
PIT/QUARRY	- ARKANSAS		
LOCATION	- SEBASTIAN, COUNTY	DATE SAMPLED	- 11/02/21
SAMPLED BY	- THORNTON/FAULKNER	DATE RECEIVED	- 11/04/21
SAMPLE FROM	- TEST HOLE	DATE TESTED	-
MATERIAL DESC.	- PAVEMENT SOUNDINGS ONLY		

LAB NUMBER	-	20212825	-	20212826	-	20212827
SAMPLE ID	-		-		-	
TEST STATUS	-	INFORMATION ONLY	-	INFORMATION ONLY	-	INFORMATION ONLY
STATION	-	17.12	-	17.12	-	17.37
LOCATION	-	06 RT	-	15 RT	-	09 LT
DEPTH IN FEET	-		-		-	
MAT'L COLOR	-		-		-	
MAT'L TYPE	-		-		-	
LATITUDE DEG-MIN-SEC	-	35 17 54.40	-	35 17 54.40	-	35 17 50.20
LONGITUDE DEG-MIN-SEC	-	94 09 16.80	-	94 09 16.80	-	94 09 1.90
% PASSING	2 IN.	-	-	-	-	-
	1 1/2 IN.	-	-	-	-	-
	3/4 IN.	-	-	-	-	-
	3/8 IN.	-	-	-	-	-
	NO. 4	-	-	-	-	-
	NO. 10	-	-	-	-	-
	NO. 40	-	-	-	-	-
	NO. 80	-	-	-	-	-
	NO. 200	-	-	-	-	-
LIQUID LIMIT	-		-		-	
PLASTICITY INDEX	-		-		-	
AASHTO SOIL	-		-		-	
UNIFIED SOIL	-		-		-	
% MOISTURE CONTENT	-		-		-	
ACHMSC	(IN)	- 10.0W	-	3.0	-	5.25W
ACHMSC	(IN)	- ---	-	4.5W	-	---
ACHMBC	(IN)	- ---	-	---	-	1.5
PCCP	(IN)	- 7.0	-	---	-	7.5
AGG BASE CRS CL-5	(IN)	- ---	-	1.5	-	---
		-	-		-	
		-	-		-	
		-	-		-	
		-	-		-	

REMARKS - W=MULTIPLE LAYERS, X=STRIPPED

-
-
-
-

AASHTO TESTS : T24 T88 T89 T90 T265

:

ARKANSAS STATE HIGHWAY AND TRANSPORTATION DEPARTMENT - LITTLE ROCK, ARKANSAS
MATERIALS DIVISION

JONATHAN A. ANNABLE, MATERIALS ENGINEER

*** SOIL SURVEY / PAVEMENT SOUNDING TEST REPORT ***

DATE	- 11/05/21	SEQUENCE NO.	- 2
JOB NUMBER	- 040837	MATERIAL CODE	- PSO
FEDERAL AID NO.	- TO BE ASSIGNED	SPEC. YEAR	- 2014
PURPOSE	- SOIL SURVEY SAMPLE	SUPPLIER ID.	- 1
SPEC. REMARKS	- NO SPECIFICATION CHECK	COUNTY/STATE	- 65
SUPPLIER NAME	- STATE	DISTRICT NO.	- 04
NAME OF PROJECT	- BLOOMER - FRANKLIN CO. LINE		
PROJECT ENGINEER	- NOT APPLICABLE		
PIT/QUARRY	- ARKANSAS		
LOCATION	- SEBASTIAN, COUNTY	DATE SAMPLED	- 11/02/21
SAMPLED BY	- THORNTON/FAULKNER	DATE RECEIVED	- 11/04/21
SAMPLE FROM	- TEST HOLE	DATE TESTED	-
MATERIAL DESC.	- PAVEMENT SOUNDINGS ONLY		

LAB NUMBER	- 20212828	- 20212829	- 20212830
SAMPLE ID	-	-	-
TEST STATUS	- INFORMATION ONLY	- INFORMATION ONLY	- INFORMATION ONLY
STATION	- 17.37	- 17.62	- 17.62
LOCATION	- 18 LT	- 15 RT	- 20 RT
DEPTH IN FEET	-	-	-
MAT'L COLOR	-	-	-
MAT'L TYPE	-	-	-
LATITUDE DEG-MIN-SEC	- 35 17 50.20	- 35 17 45.40	- 35 17 45.40
LONGITUDE DEG-MIN-SEC	- 94 09 1.90	- 94 08 47.10	- 94 08 47.10
% PASSING	2 IN. -	-	-
	1 1/2 IN. -	-	-
	3/4 IN. -	-	-
	3/8 IN. -	-	-
	NO. 4 -	-	-
	NO. 10 -	-	-
	NO. 40 -	-	-
	NO. 80 -	-	-
	NO. 200 -	-	-
LIQUID LIMIT	-	-	-
PLASTICITY INDEX	-	-	-
AASHTO SOIL	-	-	-
UNIFIED SOIL	-	-	-
% MOISTURE CONTENT	-	-	-
ACHMSC	(IN) - 4.0W	- 1.5XW	- 3.5W
ACHMSC	(IN) - ---	- 1.5X	- 0.25X
ACHMSC	(IN) - ---	- 1.0	- 2.25
ACHMSC	(IN) - ---	- 2.5	- ---
ACHMSC	(IN) - ---	- 1.5X	- ---
ACHMBC	(IN) - ---	- 6.0X	- ---
AGG BASE CRS CL-5	(IN) - 1.5	- ---	- ---
	-	-	-
	-	-	-

REMARKS - W=MULTIPLE LAYERS, X=STRIPPED

-
-
-
-

AASHTO TESTS : T24 T88 T89 T90 T265

:

ARKANSAS STATE HIGHWAY AND TRANSPORTATION DEPARTMENT - LITTLE ROCK, ARKANSAS
MATERIALS DIVISION

JONATHAN A. ANNABLE, MATERIALS ENGINEER

*** SOIL SURVEY / PAVEMENT SOUNDING TEST REPORT ***

DATE	- 11/05/21	SEQUENCE NO.	- 3
JOB NUMBER	- 040837	MATERIAL CODE	- PSO
FEDERAL AID NO.	- TO BE ASSIGNED	SPEC. YEAR	- 2014
PURPOSE	- SOIL SURVEY SAMPLE	SUPPLIER ID.	- 1
SPEC. REMARKS	- NO SPECIFICATION CHECK	COUNTY/STATE	- 65
SUPPLIER NAME	- STATE	DISTRICT NO.	- 04
NAME OF PROJECT	- BLOOMER - FRANKLIN CO. LINE		
PROJECT ENGINEER	- NOT APPLICABLE		
PIT/QUARRY	- ARKANSAS		
LOCATION	- SEBASTIAN, COUNTY	DATE SAMPLED	- 11/02/21
SAMPLED BY	- THORNTON/FAULKNER	DATE RECEIVED	- 11/04/21
SAMPLE FROM	- TEST HOLE	DATE TESTED	-
MATERIAL DESC.	- PAVEMENT SOUNDINGS ONLY		

LAB NUMBER	- 20212831	- 20212832	- 20212833
SAMPLE ID	-	-	-
TEST STATUS	- INFORMATION ONLY	- INFORMATION ONLY	- INFORMATION ONLY
STATION	- 17.87	- 17.87	- 18.12
LOCATION	- 15 LT	- 20 LT	- 15 RT
DEPTH IN FEET	-	-	-
MAT'L COLOR	-	-	-
MAT'L TYPE	-	-	-
LATITUDE DEG-MIN-SEC	- 35 17 41.10	- 35 17 41.20	- 35 17 37.00
LONGITUDE DEG-MIN-SEC	- 94 08 32.10	- 94 08 32.10	- 94 08 17.10
% PASSING	2 IN. -	-	-
	1 1/2 IN. -	-	-
	3/4 IN. -	-	-
	3/8 IN. -	-	-
	NO. 4 -	-	-
	NO. 10 -	-	-
	NO. 40 -	-	-
	NO. 80 -	-	-
	NO. 200 -	-	-
LIQUID LIMIT	-	-	-
PLASTICITY INDEX	-	-	-
AASHTO SOIL	-	-	-
UNIFIED SOIL	-	-	-
% MOISTURE CONTENT	-	-	-
ACHMSC	(IN) - 2.5W	- 4.5W	- 3.0
ACHMSC	(IN) - 0.25X	- 0.25X	- 0.25X
ACHMSC	(IN) - 1.5	- 1.75	- 1.5
ACHMSC	(IN) - 0.25X	- ---	- 1.25X
ACHMBC	(IN) - 4.0W	- ---	- 1.5
ACHMBC	(IN) - ---	- ---	- 1.0X
ACHMBC	(IN) - ---	- ---	- 2.75
	-	-	-
	-	-	-

REMARKS - W=MULTIPLE LAYERS, X=STRIPPED

-
-
-
-

AASHTO TESTS : T24 T88 T89 T90 T265

:

ARKANSAS STATE HIGHWAY AND TRANSPORTATION DEPARTMENT - LITTLE ROCK, ARKANSAS
MATERIALS DIVISION

JONATHAN A. ANNABLE, MATERIALS ENGINEER

*** SOIL SURVEY / PAVEMENT SOUNDING TEST REPORT ***

DATE	- 11/05/21	SEQUENCE NO.	- 4
JOB NUMBER	- 040837	MATERIAL CODE	- PSO
FEDERAL AID NO.	- TO BE ASSIGNED	SPEC. YEAR	- 2014
PURPOSE	- SOIL SURVEY SAMPLE	SUPPLIER ID.	- 1
SPEC. REMARKS	- NO SPECIFICATION CHECK	COUNTY/STATE	- 65
SUPPLIER NAME	- STATE	DISTRICT NO.	- 04
NAME OF PROJECT	- BLOOMER - FRANKLIN CO. LINE		
PROJECT ENGINEER	- NOT APPLICABLE		
PIT/QUARRY	- ARKANSAS		
LOCATION	- SEBASTIAN, COUNTY	DATE SAMPLED	- 11/02/21
SAMPLED BY	- THORNTON/FAULKNER	DATE RECEIVED	- 11/04/21
SAMPLE FROM	- TEST HOLE	DATE TESTED	-
MATERIAL DESC.	- PAVEMENT SOUNDINGS ONLY		

LAB NUMBER	-	20212834	-	20212835	-	20212836
SAMPLE ID	-	-	-	-	-	-
TEST STATUS	-	INFORMATION ONLY	-	INFORMATION ONLY	-	INFORMATION ONLY
STATION	-	18.12	-	18.56	-	18.56
LOCATION	-	20 RT	-	06 RT	-	15 RT
DEPTH IN FEET	-	-	-	-	-	-
MAT'L COLOR	-	-	-	-	-	-
MAT'L TYPE	-	-	-	-	-	-
LATITUDE DEG-MIN-SEC	-	35 17 37.00	-	35 17 33.80	-	35 17 33.80
LONGITUDE DEG-MIN-SEC	-	94 08 17.10	-	94 07 49.60	-	94 07 49.70
% PASSING	2 IN.	-	-	-	-	-
	1 1/2 IN.	-	-	-	-	-
	3/4 IN.	-	-	-	-	-
	3/8 IN.	-	-	-	-	-
	NO. 4	-	-	-	-	-
	NO. 10	-	-	-	-	-
	NO. 40	-	-	-	-	-
	NO. 80	-	-	-	-	-
	NO. 200	-	-	-	-	-
LIQUID LIMIT	-	-	-	-	-	-
PLASTICITY INDEX	-	-	-	-	-	-
AASHTO SOIL	-	-	-	-	-	-
UNIFIED SOIL	-	-	-	-	-	-
% MOISTURE CONTENT	-	-	-	-	-	-
ACHMSC	(IN)	5.0W	-	4.0W	-	1.75
ACHMSC	(IN)	0.25X	-	6.0W	-	5.75X
ACHMSC	(IN)	3.0W	-	---	-	---
PCCP	(IN)	---	-	6.75	-	---
	-	-	-	-	-	-
	-	-	-	-	-	-
	-	-	-	-	-	-
	-	-	-	-	-	-
	-	-	-	-	-	-

REMARKS - W=MULTIPLE LAYERS, X=STRIPPED

-
-
-
-

AASHTO TESTS : T24 T88 T89 T90 T265

:

ARKANSAS STATE HIGHWAY AND TRANSPORTATION DEPARTMENT - LITTLE ROCK, ARKANSAS
MATERIALS DIVISION

JONATHAN A. ANNABLE, MATERIALS ENGINEER

*** SOIL SURVEY / PAVEMENT SOUNDING TEST REPORT ***

DATE	- 11/05/21	SEQUENCE NO.	- 5
JOB NUMBER	- 040837	MATERIAL CODE	- PSO
FEDERAL AID NO.	- TO BE ASSIGNED	SPEC. YEAR	- 2014
PURPOSE	- SOIL SURVEY SAMPLE	SUPPLIER ID.	- 1
SPEC. REMARKS	- NO SPECIFICATION CHECK	COUNTY/STATE	- 65
SUPPLIER NAME	- STATE	DISTRICT NO.	- 04
NAME OF PROJECT	- BLOOMER - FRANKLIN CO. LINE		
PROJECT ENGINEER	- NOT APPLICABLE		
PIT/QUARRY	- ARKANSAS		
LOCATION	- SEBASTIAN, COUNTY	DATE SAMPLED	- 11/02/21
SAMPLED BY	- THORNTON/FAULKNER	DATE RECEIVED	- 11/04/21
SAMPLE FROM	- TEST HOLE	DATE TESTED	-
MATERIAL DESC.	- PAVEMENT SOUNDINGS ONLY		

LAB NUMBER	- 20212837	- 20212838	- 20212839
SAMPLE ID	-	-	-
TEST STATUS	- INFORMATION ONLY	- INFORMATION ONLY	- INFORMATION ONLY
STATION	- 18.70	- 18.70	- 20.16
LOCATION	- 06 LT	- 15 LT	- 06 RT
DEPTH IN FEET	-	-	-
MAT'L COLOR	-	-	-
MAT'L TYPE	-	-	-
LATITUDE DEG-MIN-SEC	- 35 17 32.70	- 35 17 32.70	- 35 17 23.90
LONGITUDE DEG-MIN-SEC	- 94 07 40.90	- 94 07 40.90	- 94 06 12.00
% PASSING	2 IN. -	-	-
	1 1/2 IN. -	-	-
	3/4 IN. -	-	-
	3/8 IN. -	-	-
	NO. 4 -	-	-
	NO. 10 -	-	-
	NO. 40 -	-	-
	NO. 80 -	-	-
	NO. 200 -	-	-
LIQUID LIMIT	-	-	-
PLASTICITY INDEX	-	-	-
AASHTO SOIL	-	-	-
UNIFIED SOIL	-	-	-
% MOISTURE CONTENT	-	-	-
ACHMSC	(IN) - 3.75W	- 3.0XW	- 4.5W
ACHMSC	(IN) - 1.0X	- 2.75	- 7.5
ACHMSC	(IN) - 6.5	- ---	- ---
PCCP	(IN) - 0.25X	- ---	- ---
PCCP	(IN) - 4.5	- ---	- ---
	-	-	-
	-	-	-
	-	-	-
	-	-	-

REMARKS - W=MULTIPLE LAYERS, X=STRIPPED

-
-
-
-

AASHTO TESTS : T24 T88 T89 T90 T265

:

ARKANSAS STATE HIGHWAY AND TRANSPORTATION DEPARTMENT - LITTLE ROCK, ARKANSAS
MATERIALS DIVISION

JONATHAN A. ANNABLE, MATERIALS ENGINEER

*** SOIL SURVEY / PAVEMENT SOUNDING TEST REPORT ***

DATE	- 11/05/21	SEQUENCE NO.	- 6
JOB NUMBER	- 040837	MATERIAL CODE	- PSO
FEDERAL AID NO.	- TO BE ASSIGNED	SPEC. YEAR	- 2014
PURPOSE	- SOIL SURVEY SAMPLE	SUPPLIER ID.	- 1
SPEC. REMARKS	- NO SPECIFICATION CHECK	COUNTY/STATE	- 65
SUPPLIER NAME	- STATE	DISTRICT NO.	- 04
NAME OF PROJECT	- BLOOMER - FRANKLIN CO. LINE		
PROJECT ENGINEER	- NOT APPLICABLE		
PIT/QUARRY	- ARKANSAS		
LOCATION	- SEBASTIAN, COUNTY	DATE SAMPLED	- 11/02/21
SAMPLED BY	- THORNTON/FAULKNER	DATE RECEIVED	- 11/04/21
SAMPLE FROM	- TEST HOLE	DATE TESTED	-
MATERIAL DESC.	- PAVEMENT SOUNDINGS ONLY		

LAB NUMBER	- 20212840	- 20212841	- 20212842
SAMPLE ID	-	-	-
TEST STATUS	- INFORMATION ONLY	- INFORMATION ONLY	- INFORMATION ONLY
STATION	- 20.16	- 20.41	- 20.41
LOCATION	- 15 RT	- 06 LT	- 15 LT
DEPTH IN FEET	-	-	-
MAT'L COLOR	-	-	-
MAT'L TYPE	-	-	-
LATITUDE DEG-MIN-SEC	- 35 17 23.80	- 35 17 25.00	- 35 17 25.10
LONGITUDE DEG-MIN-SEC	- 94 06 12.00	- 94 05 56.70	- 94 05 56.80
% PASSING	2 IN. -	-	-
	1 1/2 IN. -	-	-
	3/4 IN. -	-	-
	3/8 IN. -	-	-
	NO. 4 -	-	-
	NO. 10 -	-	-
	NO. 40 -	-	-
	NO. 80 -	-	-
	NO. 200 -	-	-
LIQUID LIMIT	-	-	-
PLASTICITY INDEX	-	-	-
AASHTO SOIL	-	-	-
UNIFIED SOIL	-	-	-
% MOISTURE CONTENT	-	-	-
ACHMSC	(IN) - 5.0W	- 8.0W	- 7.0WX
ACHMSC	(IN) - 3.5	- ---	- 0.25X
ACHMSC	(IN) - 1.5X	- ---	- 2.0
ACHMBC	(IN) - ---	- 3.0	- 2.5
	-	-	-
	-	-	-
	-	-	-
	-	-	-
	-	-	-

REMARKS - W=MULTIPLE LAYERS, X=STRIPPED

-
-
-
-

AASHTO TESTS : T24 T88 T89 T90 T265

:

ARKANSAS STATE HIGHWAY AND TRANSPORTATION DEPARTMENT - LITTLE ROCK, ARKANSAS
MATERIALS DIVISION

JONATHAN A. ANNABLE, MATERIALS ENGINEER

*** SOIL SURVEY / PAVEMENT SOUNDING TEST REPORT ***

DATE	- 11/05/21	SEQUENCE NO.	- 7
JOB NUMBER	- 040837	MATERIAL CODE	- PSO
FEDERAL AID NO.	- TO BE ASSIGNED	SPEC. YEAR	- 2014
PURPOSE	- SOIL SURVEY SAMPLE	SUPPLIER ID.	- 1
SPEC. REMARKS	- NO SPECIFICATION CHECK	COUNTY/STATE	- 65
SUPPLIER NAME	- STATE	DISTRICT NO.	- 04
NAME OF PROJECT	- BLOOMER - FRANKLIN CO. LINE		
PROJECT ENGINEER	- NOT APPLICABLE		
PIT/QUARRY	- ARKANSAS		
LOCATION	- SEBASTIAN, COUNTY		
SAMPLED BY	- THORNTON/FAULKNER	DATE SAMPLED	- 11/02/21
SAMPLE FROM	- TEST HOLE	DATE RECEIVED	- 11/04/21
MATERIAL DESC.	- PAVEMENT SOUNDINGS ONLY	DATE TESTED	-

LAB NUMBER	-	20212843	-	20212844	-	20212845	
SAMPLE ID	-	-	-	-	-	-	
TEST STATUS	-	INFORMATION ONLY	-	INFORMATION ONLY	-	INFORMATION ONLY	
STATION	-	20.66	-	20.66	-	20.91	
LOCATION	-	15 RT	-	20 RT	-	15 LT	
DEPTH IN FEET	-	-	-	-	-	-	
MAT'L COLOR	-	-	-	-	-	-	
MAT'L TYPE	-	-	-	-	-	-	
LATITUDE DEG-MIN-SEC	-	35 17 29.70	-	35 17 29.70	-	35 17 34.70	
LONGITUDE DEG-MIN-SEC	-	94 05 41.90	-	94 05 41.90	-	94 05 27.30	
% PASSING	2	IN.	-	-	-	-	
	1 1/2	IN.	-	-	-	-	
	3/4	IN.	-	-	-	-	
	3/8	IN.	-	-	-	-	
	NO. 4	-	-	-	-	-	
	NO. 10	-	-	-	-	-	
	NO. 40	-	-	-	-	-	
	NO. 80	-	-	-	-	-	
	NO. 200	-	-	-	-	-	
LIQUID LIMIT	-	-	-	-	-	-	
PLASTICITY INDEX	-	-	-	-	-	-	
AASHTO SOIL	-	-	-	-	-	-	
UNIFIED SOIL	-	-	-	-	-	-	
% MOISTURE CONTENT	-	-	-	-	-	-	
ACHMSC	(IN)	-	1.75XW	-	7.5W	-	3.0W
ACHMSC	(IN)	-	5.5X	-	---	-	0.25X
ACHMSC	(IN)	-	---	-	---	-	5.0
ACHMBC	(IN)	-	2.5W	-	---	-	---
ACHMBC	(IN)	-	6.0XW	-	---	-	---
ACHMBC	(IN)	-	3.0	-	---	-	---
	-	-	-	-	-	-	-
	-	-	-	-	-	-	-
	-	-	-	-	-	-	-

REMARKS - W=MULTIPLE LAYERS, X=STRIPPED

-
-
-
-

AASHTO TESTS : T24 T88 T89 T90 T265

:

ARKANSAS STATE HIGHWAY AND TRANSPORTATION DEPARTMENT - LITTLE ROCK, ARKANSAS
MATERIALS DIVISION

JONATHAN A. ANNABLE, MATERIALS ENGINEER

*** SOIL SURVEY / PAVEMENT SOUNDING TEST REPORT ***

DATE	- 11/05/21	SEQUENCE NO.	- 8
JOB NUMBER	- 040837	MATERIAL CODE	- PSO
FEDERAL AID NO.	- TO BE ASSIGNED	SPEC. YEAR	- 2014
PURPOSE	- SOIL SURVEY SAMPLE	SUPPLIER ID.	- 1
SPEC. REMARKS	- NO SPECIFICATION CHECK	COUNTY/STATE	- 65
SUPPLIER NAME	- STATE	DISTRICT NO.	- 04
NAME OF PROJECT	- BLOOMER - FRANKLIN CO. LINE		
PROJECT ENGINEER	- NOT APPLICABLE		
PIT/QUARRY	- ARKANSAS		
LOCATION	- SEBASTIAN, COUNTY	DATE SAMPLED	- 11/02/21
SAMPLED BY	- THORNTON/FAULKNER	DATE RECEIVED	- 11/04/21
SAMPLE FROM	- TEST HOLE	DATE TESTED	-
MATERIAL DESC.	- PAVEMENT SOUNDINGS ONLY		

LAB NUMBER	-	20212846	-	20212847	-	20212848
SAMPLE ID	-		-		-	
TEST STATUS	-	INFORMATION ONLY	-	INFORMATION ONLY	-	INFORMATION ONLY
STATION	-	20.91	-	21.16	-	21.16
LOCATION	-	20 LT	-	15 RT	-	20 RT
DEPTH IN FEET	-		-		-	
MAT'L COLOR	-		-		-	
MAT'L TYPE	-		-		-	
LATITUDE DEG-MIN-SEC	-	35 17 34.90	-	35 17 38.80	-	35 17 38.60
LONGITUDE DEG-MIN-SEC	-	94 05 27.30	-	94 05 12.20	-	94 05 12.10
% PASSING						
	2	IN.	-		-	
	1 1/2	IN.	-		-	
	3/4	IN.	-		-	
	3/8	IN.	-		-	
	NO. 4		-		-	
	NO. 10		-		-	
	NO. 40		-		-	
	NO. 80		-		-	
	NO. 200		-		-	
LIQUID LIMIT	-		-		-	
PLASTICITY INDEX	-		-		-	
AASHTO SOIL	-		-		-	
UNIFIED SOIL	-		-		-	
% MOISTURE CONTENT	-		-		-	
ACHMSC	(IN)	8.25W	-	1.75XW	-	6.5W
ACHMSC	(IN)	---	-	0.25X	-	---
ACHMSC	(IN)	---	-	4.0	-	---
BST	(IN)	0.25	-	---	-	---
			-		-	
			-		-	
			-		-	
			-		-	
			-		-	
			-		-	

REMARKS - W=MULTIPLE LAYERS, X=STRIPPED

-
-
-
-

AASHTO TESTS : T24 T88 T89 T90 T265

:













